

1 Product description:

Bitumen 30-40

Specification	Value	Test Method
Specific Gravity @ 25/25 deg. C.	1.01/1.06	ASTM D.70
Penetration @ 25 deg. C.	30/40	ASTM D.5
Softening Point deg. C.	55/63	ASTM D.36
Ductility @ 25 deg. C. CMS	100 min.	ASTM D.113
Loss on heating PCT. WT.	0.2 max.	ASTM D.6
Drop in penetration after heating PCT.	20 max.	ASTM D.5
Solubility in CS ₂ PCT. WT.	99.5 max.	ASTM D.4
Organic matter insoluble in CS ₂ PCT. WT.	0.2 max.	ASTM D.4