



VIRA PROSHOT

–Oil & Petrochemical–

KİMYA SANAYİ VE DIŞ TİCARET LTD.

V I R A P R O S H O T O I L & P E T R O C H E M I C A L C O M P A N Y

1 Product description:

Bitumen 60-70

Specification	Value	Test Method
Specific Gravity @ 25/25 deg. C.	1.01/1.06	ASTM D.70
Penetration @ 25 deg. C.	60/70	ASTM D.5
Softening Point deg. C.	49/56	ASTM D.36
Ductility @ 25 deg. C. CMS	100 min.	ASTM D.113
Loss on heating PCT. WT.	0.2 max.	ASTM D.6
Drop in penetration after heating PCT.	20 max.	ASTM D.5
Flash point deg. C.	250 min.	ASTM D.92
Solubility in CS ₂ PCT. WT.	99.5 max.	ASTM D.4
Organic matter insoluble in CS ₂ PCT. WT.	0.2 max.	ASTM D.4

VIRA PROSHOT KİMYA SANAYİ VE DIŞ TİCARET LİMİTED ŞİRKETİ

Adres : ZÜHTÜPAŞA MAH. ŞEFİKBEY SK. NO: 3 Kadıköy, İstanbul – Türkiye Post Code : 34724

İLETİŞİM WhatsApp: +90 535 1066554 Sabit No : +90 532 2815425