

## 1 Product description:

Bitumen 85-100

| Specification  | Value     | Test Method |
|--|-----------|-------------|
| Specific Gravity @ 25/25 deg. C.                     | 1.01/1.05 | ASTM D.70   |
| Penetration @ 25 deg. C.                             | 85/100    | ASTM D.5    |
| Softening Point deg. C.                              | 45/52     | ASTM D.36   |
| Ductility @ 25 deg. C. CMS                           | 100 min.  | ASTM D.113  |
| Loss on heating PCT. WT.                             | 0.2 max.  | ASTM D.6    |
| Drop in penetration after heating PCT.               | 20 max.   | ASTM D.5    |
| Flash point deg. C.                                  | 250 min.  | ASTM D.92   |
| Solubility in CS <sub>2</sub> PCT. WT.               | 99.5 max. | ASTM D.4    |
| Organic matter insoluble in CS <sub>2</sub> PCT. WT. | 0.2 max.  | ASTM D.4    |

VİRA PROSHOT KİMYA SANAYİ VE DİŐ TİCARET LİMİTED ŐİRKETİ

Adres : ZÜHTÜPAŐA MAH. ŐEFİKBEY SK. NO: 3 Kadıköy, İstanbul – Türkiye Post Code : 34724