

1 Product description:

Acrylonitrile - Butadiene - Styrene(ABS)

2 Technical Data

◆ Data sheet ◆ MSDS ◆ S.S.S.

Grade	MFI(gr/10min) (5kg)	Vicat Softening Point (5kg)	Izod Impact (kgf.cm/cm)	Typical Application
HR2320	1.2	103	20	Automotive Parts, Heat Resistant Home Appliances
HR2340	1	112	40	Automotive Parts, Heat Resistant Home Appliances
HR0370	1.2	102	17	Automotive Interior, Cockpit Module Parts Power Window Switch Panel, Pull Handle
SD0140	3.2	97	23	Office Supplies, Home Appliances Casing
SD0150	1.7	99	22	General Injection, Home Appliances Casing
SD0152	2.4	99	23	General Injection, Home Appliances Casing
SV0157	0.5	100.5	31	Extrusion, Refrigerator Liners
SH0150	1.1	100	22	Parts with Significant Impact Resistance General Sheets
VH0800D	5.8	85	15.5	TV Monitor, Wiring Devices
HM0560	2.5	107	13	Watches, Toys, Cassette Recorders etc.

*S.S.S; Standard Sales Specification(Guaranteed Items)

General Note:

Abbreviation of LN in printed area on final product bag is as follow mean:

LN: LOT NUMBER

VIRA PROSHOT KİMYA SANAYİ VE DİŐ TİCARET LİMİTED ŐİRKETİ

Adres : ZÜHTÜPAŐA MAH. ŐEFİKBEY SK. NO: 3 Kadıköy, İstanbul – Türkiye Post Code : 34724

İLETİŐİM

WhatsApp: +90 535 1066554

Sabit No : +90 532 2815425