

1 Product description:

GENERAL PURPOSE POLYSTYRENE(GPPS)

2 Technical Data

◆ Data sheet ◆ MSDS ◆ S.S.S.

Grade	MFI(gr/10min) (5kg)	Vicat Softening Point (5kg)	Typical Application
GPPS1540	11	91	Disposable Cups Food Containers Pen bodies
GPPS1160	2.5	104	Foamed Sheet for Thermoforming, Shower cabinets
GPPS1540B	11	91	Disposable Cups & Food Containers
GPPS1460	6	103	Extrusion, Foamed Sheet for Tray
GPPS1070	1.7	104	Ultra HMW for special extrusion
GPPS1240	2.5	96	Ultra HMW for special extrusion, Impact dilution special injection molding
GPPS1340	4	97	Sheet and profile extrusion, Packaging Dilution of impact grades for extrusion, Injection molding
GPPS1810	20	10	Petri dishes, Blood Sample tubes, Disposable beakers, Thin wall moldings

*S.S.S; Standard Sales Specification(Guaranteed Items)

General Note:

Abbreviation of PS and LNG in printed area on final product bag is as follow means:

PS: PARVANEH SAKHT

LNG: LOT NUMBER

VİRA PROSHOT KİMYA SANAYİ VE DIŞ TİCARET LİMİTED ŞİRKETİ
Adres : ZÜHTÜPAŞA MAH. ŞEFİKBEY SK. NO: 3 Kadıköy, İstanbul – Türkiye Post Code : 34724