

## 1 Grade/Product Name

HF4760(THE/THT:Grade)

## 2 Main Application

Small blow moulding

Test/Composition	Method	Unit	Value
Density	ISO 1183	g/cm <sup>3</sup>	0.95 6 ±0.002
MFR(190°/21.16)	ISO 1133	g/10min	23±4
MFR(190°/5)	ISO 1133	g/10min	1.2±0.3
Notched Impact (23°c) <sup>2</sup>	ISO179/1eA	mJ/mm <sup>2</sup>	≥9

Notes:

ISO179/1eA

1- FRR values are statistical and calculated by dividing MFR values.

2- Notch Impact Test specimen from compressed moulded sheet 23°C and The data quoted is average values

**VIRA PROSHOT KİMYA SANAYİ VE DİŐ TİCARET LİMİTED ŐİRKETİ**

Adres : ZÜHTÜPAŐA MAH. ŐEFİKBEY SK. NO: 3 Kadıköy, İstanbul – Türkiye Post Code : 34724